

### Description

EW 6627 is a two-part epoxy adhesive. It is ideal for or component bonding and reinforcement on PCBs, power supply, LED etc.

### Features

- Recommended substrates: glass, aluminum, stainless steel, PC, PCB
- Excellent electrical resistance and environmental resistance
- Thixotropic
- Good toughness

### Uncured Properties

<b>Chemical Type</b>	Epoxy
<b>Appearance</b>	
Part A	Milky
Part B	Milky
<b>Viscosity @ 25°C [mPa·s]</b>	
Brookfield DV2T, spindle 14# @ 20rpm	
Part A	Paste
Part B	Paste
Mixed	Paste
<b>Mix Ratio A:B</b>	
By Volume	1:1
<b>Specific Gravity [g/cm<sup>3</sup>]</b>	
Part A	1.19
Part B	1.07
<b>Shelf Life @ 10-28°C [months]</b>	6

### Curing Conditions

<b>Setting Time [mins]</b>	30
@ 25°C (30g adhesive mixed)	
<b>Full Strength</b>	
@ 25°C [hrs]	24
@ 80°C [mins]	30

### Cured Properties

<b>Hardness [Shore D]</b>	72
ASTM D2240	
<b>Lap Shear Strength [MPa]</b>	15
Al/Al	
ASTM D1002	
<b>Elongation at Break [%]</b>	5
ASTM D638	
<b>Thermal Conductivity [W/m·k]</b>	0.3
ASTM D2214	
<b>Surface Resistivity [ohm·cm]</b>	>1.0x10 <sup>14</sup>
ASTM D257	
<b>Volume Resistivity [ohm·cm]</b>	>1.0x10 <sup>14</sup>
ASTM D257	
<b>Dielectric Strength [V/mil]</b>	300
ASTM D149	

### Directions for Use

#### 1. Surface Treatment

Surfaces to be bonded should be free of dust, oil, grease or any other contaminants in order to achieve a reproducible bond. For slightly contaminated surfaces, it is sufficient to wipe with isopropanol or ethanol. Substrates with a low surface energy (e.g. polyethylene, polypropylene, Teflon) need to be pre-treated physically (e.g. atmospheric plasma or corona) in order to achieve sufficient adhesion.

#### 2. Application

Products are supplied ready for use. Depending on package type, they can be dosed manually, semi-automatically or fully-automatically with a dosage apparatus. With automatic dispensing using a cartridge, the adhesive is conveyed via pressure and a piston rod to a dispense valve. With bottles, the adhesive is conveyed using a pump.

After application, it is recommended that the two substrates be adjoined immediately as it is possible the curing process will begin with select products under ambient conditions.

3. Suggested working temperature range is -40 to 150°C.

### Storage

Maximum shelf life may be obtained when product is stored in a cool, dry location at a temperature between **10°C to 28°C**.

TO PREVENT CONTAMINATION OF UNUSED PRODUCT, DO NOT RETURN ANY PRODUCT TO ITS ORIGINAL CONTAINER.

### Materials Handling

Refer to the Material Safety Data Sheet (MSDS) for this product.

#### *Disclaimer*

*The information provided here including the recommendations for use and application of the product is based on internal laboratory test conditions and should only be used as a reference. CollTech does not assume responsibility for the test or performance results obtained by the user. It is the responsibility of the user to perform their own evaluations to confirm whether this product is suitable for their application.*